

MASTERTILE[®] 200

Multi use water resistant latex additive and bonding agent for cementitious mortars

Description

MASTERTILE[®] 200 is a specially formulated latex additive, for use with Portland cement and sand to form high strength mortars for the installation of ceramic, wall, floor, marble, mosaic or quarry tiles, slip brick, natural or artificial stone.

Primary uses

MASTERTILE[®] 200 is used wherever increased abrasion, water and chemical resistance is required. For swimming pools, dairies, food processing factories, abattoirs, etc.

It may be used to enhance the properties of sand/cement mortars for tiling or added to MASTERTILE[®] range adhesives and grouts.

Used as an additive with MASTERTILE[®] adhesives, a degree of flexibility is imparted, improving the adhesive's suitability for use where road traffic or machine vibration is indicated. Consult your BASF representative for dosage rates.

Advantages

- Increased adhesion.
- Improves flexibility.
- Chemical resistance.
- Resistance to impact and thermal shock.
- Water resistant.
- Economical.
- Non-toxic.

Packaging

MASTERTILE[®] 200 is available in 210 litre drums.

Composition

A synthetic rubber emulsion containing hydrophilic additives, fungicides and defoaming agents.

Typical properties*

For a 3:1 sand:cement mortar modified with MASTERTILE[®] 200:

Appearance:	High viscosity white liquid
Specific gravity:	1.01 at 20°C
Compressive strength (dependent on quality of sand utilised):	40N/mm ²
Tensile strength:	6.5N/mm ²
Flexural strength:	13 N/mm ²
Shear strength:	6 N/mm ²
Freeze thaw resistance:	Excellent
Adhesion:	Excellent to concrete, brick, steel, glass, marble, ceramics, etc.
Coefficient of thermal expansion:	
-20 to + 20°C	12.8 x 10 ⁻⁶
+20 to + 60°C	12.9 x 10 ⁻⁶
Shrinkage during cure:	0.01%
Resistance to water at -3 m head:	No water penetration.
Water absorption BS 1881:	< 2%
Water vapour permeability:	Reduced by 96%
Pot life of mixed mortar:	Approx. 3 hours at 35°C
Toxicity:	MASTERTILE [®] 200 modified mixes are non-toxic after cure, and can be safely used in conjunction with potable water.
Chemical resistance:	Excellent to alkalis, dilute acids, milk, sewage effluent, mineral oils, etc.

Note: values given are those achieved under controlled conditions with cement and sands of known quality. Different results may be obtained under site conditions.

MASTERTILE[®] 200

Application procedure

Surface preparation:

As with all bonding materials surface preparation is of paramount importance. Remove all laitance, oil, grease, mould oil, curing compound, leaving an open textured surface. Damp down the surface prior to application of MASTERTILE[®] 200 modified mortars, ensuring surface is damp, but no free water is visible.

Mixing:

All mixing should be carried out in a forced action mixer although hand mixing is acceptable where the total weight of mix does not exceed 25kg. Charge the mixer with the correct quantity of sand and cement, and premix for one minute. Pour in the desired quantity of MASTERTILE[®] 200 (premixed with water if necessary), and mix for 3 minutes. Owing to the strong plasticising action of MASTERTILE[®] 200 care should be taken to ensure prolonged mixing does not occur. Material will remain workable for at least 3 hours at 35°C. Where possible protect mixed material from wind, or direct sun.

Application:

Apply to surface using notched trowel technique. Working in areas of approximately 1 metre at a time to avoid skinning of the adhesive. Set dry tiles in bed of mortar, and slightly twist to ensure good adhesion. When tiles are aligned in final position lightly tap using a wooden float. Allow tiles to set for 24 hours before grouting. Alternatively, especially when tile fixing in permanently wet conditions, or fixing heavy decorative cladding, solid bed fixing is recommended. Apply solid bed to required depth, and "push" the tiles into place. Ensure that the ribs on the back of the tiles are filled in using buttering techniques. This will ensure 100% contact of adhesive.

Watchpoints

Expansion joints:

Wherever tiles are being laid over existing concrete surfaces it is important that expansion joints in the subfloor or background are carried through the MASTERTILE[®] 200 modified mortar. This can be done by fitting a temporary timber batten wrapped in one layer of polyethylene.

Minimum width of expansion joints should be 6.5mm. Seal the joint after tiling using MASTERFLEX BACKER ROD followed by MASTERFLEX 700.

Mix design

Thin bed fixing of wall and floor tiles:

- 50 kg of cement (fresh).
- 50 kg medium grade sand.
- MASTERTILE[®] 200 10 litres.
- Water - It is normally found that a 1 / 1 dilution of MASTERTILE[®] 200 with water will prove suitable.

Yield approximately 50 litres of mortar. Materials should be mixed until a thick paste is formed.

Thick bed fixing:

- Fresh cement 50 kg.
- 150 kg of medium grade sand.
- MASTERTILE[®] 200 10 litres.



The Chemical Company

MASTERTILE[®] 200

It may be necessary to add water to achieve the desired consistency dependant upon type of sand utilised.

Yield approximately 100 litres of mortar.

Grouting

MASTERTILE[®] 200 can be utilised to produced a waterproof and chemically resistant tile grout for floor and wall tiles in swimming pools, abattoirs, animal houses, dairy farms, etc.

The proportion of sand to cement will vary with the width of joint to be grouted.

Recommended mix designs for tile grouts are as follows:-

Joint size	Fine sand	Cement	MASTERTIL E [®] 200	Yield
upto 3mm	50kg	50kg	10 litres	0.05m ³
upto 12mm	100kg	50kg	10 litres	0.75m ³
over 12mm	150kg	50kg	10 litres	0.10m ³

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Department.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All BASF Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and BASF ESHQ recommendations.

Saudi BASF – 12/2007

* Properties listed are only for guidance and are not a guarantee of performance.

Saudi BASF For Building Materials Co, .Ltd. (Saudi Arabia)

P.O Box 1884 Al-Khobar 31952 Tel: +966 3 8121140 Fax: +966 3 8121822

Web: www.saudi-basf.com

e-mail: enquirycc.saudi@basf.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.