

MASTERSEAL[®] 410

High solids protective coating based on emulsified bitumen

Description

MASTERSEAL[®] 410 is a non-fibrated, water based bitumen emulsion. It is dark brown in colour and dries to a black flexible protective coating. The finished film is tough and waterproof and forms a barrier to water and vapour transmission.

Typical applications

- General waterproofing and damp proofing of concrete, asbestos cement, roofing felt, slate tiles, wood, etc.
- Metal protection: provides protection for structural steelwork, pipes, etc.
- Insulation: provides a vapour barrier for cold storage rooms, etc.
- Protection to a variety of buried structures such as concrete foundations and retaining walls.

Advantages

- Chemical resistance.
- Versatile.
- Economical
- Easy to apply.
- Cold applied.

Packaging

MASTERSEAL[®] 410 is available in 200 litre drums.

Composition

A blend of selected asphalts and bitumens emulsified in water.

Application procedure

Surface preparation:

Ensure surface to be treated is sound and free of all oil, grease or conventional curing compounds. MASTERSEAL[®] 410 can be applied directly to concrete surfaces cured utilising non-degradable curing compounds such as MASTERKURE 181.

If the surface is dusty it should be primed with a coat of MASTERSEAL[®] 410 diluted with an equal quantity of clean water and allowed to dry, before applying further coats of MASTERSEAL[®] 410. MASTERSEAL[®] 410 can be applied to damp surfaces, although both coating and surface must be allowed to dry before the MASTERSEAL[®] 410 will cure to form a waterproof film.

Typical properties*

Flashpoint:	Non flammable
Specific gravity:	1.00 @ 25°C
Application temperature:	5°C to 50°C
Service temperature:	-10°C to 85°C (depending on operating conditions)
Chemical resistance:	Excellent to water, dilute acids, alkalis, chloride and sulphate ions
Flexibility:	Provides a firm flexible coating

Standards

ACI 515 IR-79. Guide to use of waterproofing, damp proofing, protecting and decorative barrier systems for concrete. Chapter 2 Section 2.1.1, 2.1.2., 2.1.3.



The Chemical Company

MASTERSEAL[®] 410

Performance

Concrete coated with MASTERSEAL[®] 410 will prevent the absorption of saline solutions. On uncoated surfaces, salts in groundwater will penetrate and can cause reinforcement corrosion and concrete deterioration.

Application

Agitate before use. As settlement can occur, the drum should be rolled before decanting material.

Apply by brush, broom or squeegee. Apply one or two coats, depending on the degree of protection required. Apply subsequent coats at right angles to the first, allowing 12 to 24 hours between coats. Where being utilised to damp proof solid floors or where a screed is to be applied over MASTERSEAL[®] 410, apply a second coat at right angles and lightly grit to form a key. Allow at least 24 hours before application of concrete screed, ensuring this is greater than 50mm in thickness.

Coverage

2-4m² per litre per coat depending on substrate porosity.

Equipment care

After use, if the MASTERSEAL[®] 410 has not dried, it may be possible to clean tools using soapy water. If the MASTERSEAL[®] 410 has dried remove as much as possible by physically scraping and then remove remainder with paraffin, white spirit or CLEANING SOLVENT NO. 2.

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment. As with all bituminous emulsions, some settlement will occur with prolonged storage. It is, therefore, necessary to invert the drums monthly to disperse the settlement.

Shelf life is up to 6 months in unopened containers, when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

Safety precautions

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation. For further information refer to the material safety data sheet.



The Chemical Company

MASTERSEAL[®] 410

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All BASF Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and BASF ESHQ recommendations.

Saudi BASF – 12/2007

*Properties listed are only for guidance and are not a guarantee of performance

Saudi BASF For Building Materials Co, .Ltd. (Saudi Arabia)

P.O Box-1884 Al-Khobar 31952 Tel: +966 3 8121140 Fax: +966 3 8121822

Web: www.saudi-basf.com

e-mail: enquirycc.saudi@basf.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.